

GIADA_20 S2 SRC



DESCRIPTION	NORM EN ISO 20345:2011	RESULT	REQUIREMENT
UPPER: Micro suede leather, breathable textile	5.4.3 Tear strength	153 N	≥120 N
	5.4.6 Water vapour permeability Coefficient	1,9 mg/cm ² h 17,7 mg/cm ²	≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
VAMP LINING: Breathable, abrasion resistance	5.5.1 Tear strength	25 N	≥ 15 N
	5.5.2 Abrasion resistance(Wet)	No fori	51.200 cicli
	Abrasion resistance(Dry)	No fori	25.600 cicli
QUARTER LINING: Breathable, abrasion resistance	5.5.3 Water vapour permeability Coefficient	7.7 mg/cm ² h 62.0 mg/cm ²	≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²
	5.5.1 Tear strength	25 N	≥ 15 N
SAFETY TOE CAP: Non-metallic composite pierced composite	5.5.2 Abrasion resistance(Wet)	No holes	51.200 cicli
	Abrasion resistance(Dry)	No holes	25.600 cicli
	5.5.3 Water vapour permeability Coefficient	7.7 mg/cm ² h 62.0 mg/cm ²	≥ 2,0 mg/(cm ² h) ≥20,0 mg/cm ²
FOOTBED: Removable, cushioned, antistatic insole	5.3.2.3 Impact resistance	14,0 mm	≥ 13,5 mm
	5.3.2.4 Compression resistance	15.5 mm	≥ 13,5 mm
OUTSOLE: PU 2D SRC	5.7.4.2 Abrasion resistance(Wet)	No holes	25.600 cicli
	Abrasion resistance(Dry)	No holes	12.800 cicli
	5.8.2 Tear strength	10.5 kN/m	≥ 8 kN/m
	5.8.3 Abrasion resistance	58mm ³	≤ 150 mm ³
	5.8.4 Flexing resistance	2.5 mm	≤ 4,0 mm
	5.8.5 Hydrolysi	1.5 mm	≤ 6,0 mm
	6.4.2 Oils resistance	1.0 %	≤ 12%
	5.11 Pressed ceramic tile floor on detergent resistance		
	Flat slip	0,46	≥ 0,32
	Heel slip	0,40	≥ 0,28
Stainless steel plate on glycerine resistance	Flat slip	0,21	≥ 0,18
	Heel slip	0,16	≥ 0,13

SIZES: 35-48

MONDOPOINT: 11